



PATENT ABSTRACTS OF JAPAN

(11) Publication number: **10151347 A**(43) Date of publication of application: **09.06.98**

(51) Int. Cl. **B01J 23/68**
B01D 53/86
B01D 53/94
B01J 21/16

(21) Application number: **08312058**(22) Date of filing: **22.11.98**(71) Applicant: **SEKIYU SANGYO KASSEIKA
CENTER SAKAI CHEM IND CO
LTD**(72) Inventor: **NAKATSUJI TADAO
YASUKAWA RITSU
TABATA KEIICHI
UEDA KAZUYUKI****(54) CATALYST FOR CATALYTIC REDUCTION OF
NITROGEN OXIDE****(57) Abstract:**

PROBLEM TO BE SOLVED: To enable efficient catalytic reduction of NO_x in waste gas by carrying specified amts. of silver aluminate and W, Mo or V on a solid acid carrier and using the resultant catalyst for catalytic reduction of NO_x using hydrocarbon and/or an oxygen-contg. org. compd. as a reducing agent.

SOLUTION: Silver aluminate and at least one selected from among W, Mo and V are carried on a solid acid

carrier by 0.01-10wt.% (expressed in terms of Ag) and 0.0001-0.05wt.%, respectively, to obtain the objective catalyst for catalytic reduction of NO_x using hydrocarbon and/or an oxygen-contg. org. compd. as a reducing agent. Alumina excellent in silver aluminate carrying effect is preferably used as the solid acid carrier. The catalyst is carried on a structure made of an inert substrate by forming a catalytic layer on the surface of the structure by wash coating or other method so that the catalytic layer has $\approx 30\mu\text{m}$ thickness from the surface.

COPYRIGHT: (C)1998,JPO